



## **TECHNICAL DATA SHEET**

# Gaia™ Plastic Free Cold Paper Cups Roll Stock

## **Description**

Plastic free paper cups roll stock based on FBC\* with heat sealable and water barrier functions. The material is coated on both sides and allows the production of repulpable and recyclable cups.





## **Typical End Uses**

The rolls can be used to form disposable cups (for cold drinks) and other food service ware items. Flexographic and Rotogravure are suitable printing technologies. The rolls can easily be processed on conventional converting equipment while offering energy savings due to lower sealing temperatures.

## TYPICAL PROPERTIES

Properties		Unit	Value	Method
Total Weight		GSM	216 ± 5% to 346 ± 5%	ISO 536
FBC Weight		GSM	16 ± 5%	
Thickness		μm	300 to 440	ISO 534
Dry Tensile Strength	MD	KN/m	16.4 – 22.4	ISO1924-3
	CD	KN/m	10.3 – 15.5	
Stretch at Break	MD	%	2.71 - 3.3	ISO1924-3
	CD	%	5.9 - 6.16	
Moisture		%	7 ± 1%	ISO 287
Seal Strength		N/2cm	Fiber Tear (coated side), > 3	ASTM-F88 220°C, 1 sec, 3 bar
Bendtsen Roughness		ml/min	250 ± 5% (uncoated side)	ISO 8791-2

## CONFORMITY WITH EU DIRECTIVES

The coated material complies with EC and FDA regulations; Food Compliance Certificate is available upon request.

<sup>\*</sup> FBC stands for Functional Barrier Coating.





#### **STORAGE**

The material should be stored at temperatures between 10 to 35 °C with relative humidity between 40 to 70%, in a clean and dust free environment.

The material should be conditioned 24 hours in the production area prior to use on the machine. Use within one year from the production date.

**Important**: The information given is based on our knowledge and experience at the time of production and is given in good faith. It does not represent a guarantee or legal warranty for specific properties or for suitability for a specific use. The responsibility for testing the suitability of the product for the foreseen use lies with the purchaser. However, should there be cause for claim; liability is, in all cases, limited to the value of the goods supplied.

**Address:** Napco National, 1<sup>st</sup> Industrial Area, 3<sup>rd</sup> street, P.O. BOX 538, Dammam, Saudi Arabia Tel: 00966138459400, Fax: 00966138471435, E-mail: info@napcopaper.com, website: www.napconational.com